

Contact Manufacturer

Zhengzhou Haixu Abrasives Co.,ltd

Room 1903,No.1 Building, Songshan south road,Zhengzhou City,Henan Province,Chhina

Telephone:+86-371-60305639 Fax:+86-371-60305637

Email:sales@zzhaixu.cn

Contact :Sunshine Ma

TECHNICAL DATA SHEET

PRODUCT: CHROMITE SAND

Cr₂O₃ CONTENT: 46.0% MIN

We import crushing Chrome ore from South Africa,wash,dry ,dust cleaning,sieve and pack in China port,then export to all over the world directly.



CHROMITE SAND

PHYSICAL AND CHEMICAL INDEX

Item	Unit	Index
Cr ₂ O ₃	%	≥46.0%
SiO ₂	%	≤1.0%
FeO	%	≤26.5%
CaO	%	≤0.30%
MgO	%	≤10.0%
Al ₂ O ₃	%	≤15.5%
P	%	≤0.003%
S	%	≤0.003%
Cr/Fe		1.55:1
Bulk Density	g/cm ³	2.5-3
Color	/	Black
PH	/	7-9
The amount of the acid	/	≤ 2 ML

Percent soil	%	≤0.1
Percent Moisture	%	≤0.1
The sintered	°C	1600
Percentage of free acid present in the sand	%	0
filling density	g/cm ³	2.6
sintering point	°C	> 1,800
melting temperature	°C	2,180

PACKING: 1MT BIG BAG



AVAILABLE SIZES: 0-1mm 1-3mm AFS 25-35 AFS25-30 AFS30-35 AFS35-40 AFS40-45 AFS40-50 AFS45-55 AFS45-50 AFS50-55 AFS55-60 AFS60-65 200mesh 325mesh 400mesh etc